

PRODUCT DESCRIPTION

A solvent free, two component epoxy phenolic lining system.

INTENDED USES

Enviroline 230 is a technically advanced epoxy phenolic lining system utilizing advanced hybrid epoxy phenolic technology to give improved performance:

- Fast cure (rapid return to service in 16 hours at 77°F (25°C))
- Ultra low VOC
- Single coat application
- Excellent adhesion
- Meets AWWA Standard C210-07 performance requirements
- Certified to NSF / ANSI Standard 61 for direct contact with potable water, including commercial hot water up to 180°F (82°C)

Applications include steel and concrete lining of potable water storage tanks and pipelines.



Certified to ANSI/NSF standard 61. NSF Certification is for tanks of 500 gallons (1893 litres) or greater and pipes 10 inches (25 cm) or greater in diameter

PRACTICAL INFORMATION FOR ENVIROLINE 230

Color	Limited color range available
Gloss Level	Not applicable
Volume Solids	100%
Typical Thickness	20-50 mils (500-1250 microns) dry equivalent to 20-50 mils (500-1250 microns) wet
Theoretical Coverage	80 sq.ft/US gallon at 20 mils d.f.t and stated volume solids 2 m ² /liter at 500 microns d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors. Refer to Enviroline Application Guidelines for advice on film thickness determination
Method of Application	Plural Component Airless Spray, Airless Spray

Drying Time

			Overcoating interval with self	
Temperature	Touch Dry	Hard Dry	<i>Minimum</i>	<i>Maximum</i>
77°F (25°C)	2.5 hours	3.5 hours ¹	3.5 hours	24 hours ²

¹ Sufficient coating film strength has developed to permit the handling and movement of coated steelwork. A Shore D hardness reading of 75-80 is a recommended guideline to indicate suitability for return to service.

² If the maximum overcoating interval is exceeded it will be necessary to thoroughly abrade the surface of the lining with coarse emery paper

REGULATORY DATA

Flash Point	Mixed >199°F (93°C)	
Product Weight	12.9 lb/gal (1.55 kg/l)	
VOC	0.13 lb/gal (16 g/lt) 25 g/kg	EPA Method 24 EU Solvent Emissions Directive (Council Directive 1999/13/EC)

See Product Characteristics section.

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Where necessary, remove weld spatter and where required smooth weld seams and sharp edges.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Best performance will always be achieved when Enviroline 230 is applied to surfaces prepared by abrasive blast cleaning to Sa3 (ISO 8501-1:2007) or SSPC-SP5. Where Enviroline 230 is not to be used in high heat and/or aggressive service, preparation to Sa2½ (ISO 8501-1:2007) or SSPC-SP10 may be acceptable. Contact International Protective Coatings for further information.

A sharp, angular surface profile of 3-5 mils (75-125 microns) is recommended.

Enviroline 230 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidized area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner.

The preferred method of holding the blast standard is by dehumidification.

Concrete Surfaces

Refer to International Protective Coatings for specific recommendations.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Complete units should be stored, mixed and applied in accordance with the Enviroline Application Guidelines.	
Mix Ratio	2 part(s) : 1 part(s) by volume	
Working Pot Life	104°F (40°C) 20 minutes	
Plural component airless spray	Recommended	
Airless Spray	Recommended	Refer to Enviroline Application Guidelines for more details.
Air Spray (Pressure Pot)	Not suitable	
Brush	Suitable	Can be used for the touch-up of small areas or for stripe coating of welds and edges.
Thinner	DO NOT THIN	
Cleaner	Enviroline 71C	
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with Enviroline 71C. Once units of paint have been mixed, they should not be resealed and it is advised that after prolonged stoppages, work recommences with freshly mixed units.	
Clean Up	Clean all equipment immediately after use with Enviroline 71C. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency should depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus material and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.	

PRODUCT CHARACTERISTICS

The detailed Enviroline Application Guidelines should be consulted prior to use.

This datasheet provides general guidance on the use of Enviroline 230. Specific project requirements will be dependent upon the service end use and operating conditions of the tank or vessel. Always consult International Protective Coatings to confirm that Enviroline 230 is suitable for contact with the product to be stored.

The detailed project coating specification provided by International Protective Coatings must be followed at all times.

Stripe coating is an essential part of good working practice and as such should form part of any lining specification.

For heavily pitted or porous steel, spray apply approximately 50% of the required film thickness and follow immediately with a short nap roller or squeegee to work material into the bottom of pitted areas.

For plural component airless spray application, best results will be achieved when the product is heated prior to application; Part A (Resin) to a maximum of 140°F (60°C) and Part B (Hardener) to a maximum of 105°F (40°C). For airless spray application, best results will be achieved when each component of the product is heated prior to application to 95-100°F (35-37°C).

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

Use the following chart for preferred temperature conditions. These conditions plus adequate ventilation must be maintained throughout the curing cycle.

	<u>Substrate Temperature</u>	<u>Air Temperature</u>
Preferred	70-120°F (21-49°C)	70-100°F (21-38°C)
Minimum	55°F (13°C)	55°F (13°C)

After the coating system has cured hard, the dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the minimum applied system thickness. The coating system should be free of all pinholes or other holidays. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected. The repaired areas shall be retested and allowed to cure as specified before placing the finished lining into service.

Maximum continuous dry temperature resistance for Enviroline 230 is 250°F (121°C). Maximum continuous water immersion temperature resistance for Enviroline 230 is 180°F (82°C).

This product meets the performance requirements of AWWA Standard C210-07.

Certified to ANSI/NSF Standard 61. NSF certification is for direct potable water contact, including commercial hot water at temperatures up to 180°F (82°C), in tanks greater than 500 gallons and pipes 10 inches in diameter or greater

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

SYSTEMS COMPATIBILITY

Enviroline 230 is designed for application to correctly prepared substrates.

Enviroline 230 is designed as a single coat system. It must only be overcoated with itself should re-coats or touch-up be required.

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Enviroline Application Guidelines

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations.

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety and Environmental standards, regulations and legislation.

Proper ventilation must be provided during application and afterwards during curing (refer to product datasheets for typical curing times) to ensure safe limits and prevent fires and explosions. Forced extraction will be required in confined spaces. Ventilation and/or respiratory personal protective equipment (airfed hoods or appropriate cartridge masks) must be provided during application and curing. Take precautions to avoid skin and eye contact (overalls, gloves, goggles, masks, barrier cream, etc).

Before use, obtain, read and then follow the advice given on the Material Safety Data Sheets (Base and Curing Agent if two-pack) and the Health and Safety section of the Coatings Applications Procedures for this product.

In the event that welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

The detailed safety measures are dependent on application methods and the work environment. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product and consult International Protective Coatings.

Warning: This product contains liquid epoxies and modified polyamines and may cause skin sensitization if not used correctly.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	4 US gal	2.67 US gal	5 US gal	1.33 US gal	2 US gal
For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT	Unit Size	Part A		Part B	
	4 US gal	35.2 lb		20.8 lb	
STORAGE	Shelf Life	24 months minimum at 77°F (25°C) in original, unopened containers. Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

Important Note

The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to law) any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

Copyright © AkzoNobel, 9/21/2009.

 Copyright © AkzoNobel, 9/21/2009.

www.international-pc.com