



# TECHNICAL DATA

## PROTEC II PW POTABLE WATER TANK LINING

### Product Description

100% solids, direct to metal, fast-set, two component urethane certified per ANSI/NSF Standard 61 for use as a lining in potable water tanks. It provides a very hard, tough surface with outstanding adhesion and impact resistance. Requires plural component, heated application equipment.

### Features

- Complies with ANSI/NSF Standard 61.
- Meets FDA 21CFR 175.300 for food contact.
- Zero VOC.
- No taste or odor concerns caused by entrapped solvents.
- Convenient 1:1 mix ratio.
- Unlimited film build with single multi-pass coats.
- Excellent adhesion directly to steel and ductile iron.
- Fast curing for increased productivity and short turn around times.

### Recommended Uses

As a one or two coat direct to metal lining system for steel potable water tanks and pipes to comply with ANSI/NSF Standard 61 parameters.

### Primers

**Steel:** None.

**Other:** Contact Futura for a recommendation.

### Typical Properties

<b>Solids by Volume</b>	100%
<b>Solids by Weight</b>	100%
<b>Volatile Organic Compounds</b>	0.0 lb/gal (0 g/l)
<b>Theoretical Coverage</b>	1604 ft <sup>2</sup> @ 1 mil (3.8 m <sup>2</sup> @ 1 mm)
<b>Recommend DFT</b>	15 – 50 mils (0.4 – 1.3 mm)
<b>Number of Coats</b>	1 or more
<b>Mix Ratio</b> (by volume)	1”A” : 1”B”
<b>Flash Point</b> (PMCC) <i>Mixed</i>	311°F (68°C)
<b>Shelf Life</b> @ 60-90°F (16-32°C)	Part A 12 months Part B 12 months
<b>Color</b>	White

### Specification Data

<b>Adhesion</b> – ASTM D 4541	2900 psi
<b>Elongation</b> – ASTM D 412	< 10%
<b>Tensile Strength</b> ASTM D 412	4000 psi
<b>Impact Resistance</b> ASTM G 14 – 15 mm ball	125.4 in-lbs (1447 cm/kg)
<b>Hardness</b> – ASTM D 2240	75 Shore “D”
<b>Flexibility</b> 180° Bend over 4” mandrel 90° Bend over 4” mandrel	Pass – 30 mils @ 75°F Pass – 30 mils @ -40°F
<b>Permeability</b> – ASTM E 96 (60 mil dry film thickness)	0.0078 U.S. perms 0.0113 metric perms
<b>Accelerated Weathering</b> ASTM G 23 – Q/UV, 2500 hrs	No cracking, checking or loss of flexibility; slight chalking.
<b>Cathodic Disbondment</b> ASTM G 95 – Average Radius	30 days @ 75°F    7 mm 14 days @ 149°F    8 mm

### Ordering Information

<b>Packaging:</b>	10 gal & 110 gal kits
<b>Shipping Weight:</b>	10.5 lb/gal (4.7 kg/gal)
<b>Freight Classification:</b>	Coating Solution Non-Flammable NOIBN

# APPLICATION INFORMATION PROTEC II PW

## Surface Preparation

Remove all oil, grease or other contaminants from the surface to be coated in accordance with SSPC-SP 1.

### Steel and Cast Iron:

**Immersion and Non-Immersion:** Abrasive blast to a Near White Metal in accordance with SSPC-SP 10 and obtain a 2½ -4 mil (63-100µ) anchor pattern.

**Other:** Contact Futura for specific recommendations.

## Mixing

Power mix each component separately and thoroughly for 15 to 20 minutes to a uniform consistency. Note: This product will develop phase separation and must be mixed thoroughly prior to use.

**Extreme care must be taken to use separate mixing devices to prevent cross contamination of materials.**

## Thinning

**DO NOT THIN!**

## Pot Life

Material Temperature	Time
75°F (24°C)	< 20 seconds

**DO NOT BATCH MIX.**

## Application Conditions

	Normal	Minimum	Maximum
<b>Material*</b>	140-150°F (60-65°C)	135°F (57°C)	170°F (77°C)
<b>Surface</b>	75-90°F (24-32°C)	45°F (7°C)	120°F (49°C)
<b>Ambient</b>	75-90°F (24-32°C)	35°F (2°C)	120°F (49°C)
<b>Humidity</b>	30-50%	0%	85%

\*Materials must be preheated to 75-90°F (24-32°C) min prior to use.

## Application Equipment

### Heated Plural Component Airless (only)

- 1:1 ratio capable of producing a minimum delivery rate of 1 ¼ gallons per minute at a tip pressure of 2600-3000 psi.
- Proportioner heaters and heated hose capable of maintaining material temperatures of 135-150°F (57-65°C) at the spray tip.
- Drum heaters capable of maintaining material temperatures of 75-90°F (24-32°C) during application
- 2:1 ratio feed pumps minimum.
- Contact Futura Coatings for specific information.

## Clean Up

Use MEK or a 1:1 blend of MEK and Toluol.

## Cure Time

These times are based on a 30-50% RH. Excessive film thickness, cooler temperatures or inadequate ventilation will require longer cure times.

### Surface Temperature

	50-60°F (10-15°C)	70-80°F (21-27°C)	90-100°F (32-38°C)
<b>Surface dry</b>	4-10 minutes	3-4 minutes	½-2 minutes
<b>Hard Film</b>	10-20 minutes	5-10 minutes	5 minutes
<b>Recoat (min)</b>	4-10 minutes	3-4 minutes	½-2 minutes
<b>Recoat (max)</b>	4 hours	2 hours	30 minutes
<b>Full cure</b>	3 days	2 days	24 hours

- If the maximum recoat time has been exceeded contact Futura Coatings for recommended recoat procedure.

## Repair

- Futura recommends that repairs or touch-up be completed using **Protec II PW**.
- **Pipemate PW** is the recommended repair material when plural component spray equipment is not available.
- Contact Futura for specific information.

## Safety Information

- Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
- Do not apply material in enclosed areas without adequate air exchange and ventilation.
- All application personnel must use fresh air respirators or fresh air hoods.
- Wear protective clothing, gloves and eye protection.
- Breathing fumes or contact with the skin may cause severe allergic reactions.
- This product is intended for industrial use by properly trained professional applicators only.

## Storage Conditions

- Urethane coatings need to be protected from moisture contamination. Store drums and pails in a dry location at 60-90°F (16-32°C).
- Drums **must** be kept sealed at all times with a positive feed dry air, nitrogen blanket or desiccant cartridge system.
- Materials **MUST** be kept above **50°F (10°C)**.

FUTURA COATINGS, INC., 9200 LATTY AVENUE, HAZELWOOD (ST. LOUIS), MO 63042, (314) 521-4100 FAX: (314) 521-7255

As Futura Coatings, Inc. has no control over the use to which others may put the material, it does not claim or warrant that in your particular circumstance the results you will obtain from the use of the product will be the same as those depicted in this communication, or that you will find the information or recommendations complete or accurate. Futura Coatings accepts no liability, in negligence or otherwise, for any damage resulting from your reliance on the information or recommendations in this communication. You are responsible to determine if the material is suitable for your particular purpose. We do not assume liability or responsibility of the product relative to coverage, performance or injury resulting from its use. © FUTURA COATINGS, INC. 2000