

The most widely used girth weld protection system for three-layer coated pipes.

Product description

HTLP80 field-joint coatings.

Construction: Three-layer system:

First layer: Liquid epoxy, solvent-free two-component.

Second layer: High shear strength copolymer adhesive.

Third layer: Radiation cross-linked, high density polyethylene with **PCI** (Permanent Change Indicator).

The HTLP80 system is a wrap-around heat-shrinkable sleeve which replicates the structure and performance of mill-applied three-layer PE coatings. HTLP80 also has excellent compatibility and has been extensively used on many other mill-applied coatings (see below). By far the majority of the girth welds worldwide on three-layer coated pipes, diameters up to 100" (DN2500), have been coated with HTLP80.

During installation, the epoxy is applied to the prepared pipe surface and the heat-shrinkable sleeve is immediately wrapped around the joint over the wet epoxy. Heat is then applied to the sleeve which shrinks to form a tight fit around the joint. While curing, the epoxy forms strong mechanical and chemical bonds to the pipe surface & to the copolymer adhesive layer. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

Product features/benefits

- Fully resistant to shear forces induced by soil and thermal movements**
The HTLP is tough & lasts as long a 3-layer, mill-applied coating.
- Sleeve applied over wet epoxy---allowing formation of strong mechanical & chemical bonds**
Allows fast application, combined with high performance!
- Superior cathodic disbondment and hot water immersion resistance**
Offers the optimum barrier protection against corrosion.
- Fully reconstructs the coating of three-layer coated pipes**
Thus, the HTLP allows the pipeline to have a virtually monolithic coating system.
- Dimpled backing provides a "permanent change" indicator for application of heat**
Ensures correct application heat & allows easy post-heat inspection.
Reliable inspectability at any time.

Product selection guide

	HTLP80
Max operating temperature	85°C (185°F)
Compatible line coatings	PE, FBE, Coal Tar, DFBE
Min preheat temperature	70°C (158°F)
Recommended pipe preparation	SA 2½
Soil stress restrictions	None
Performance	EN 12068 Class C60 UV Class C80 UV

Product thickness

	/B	/1.2-1	/1.4-1	/1-1.5	/C	/1.4-1.8
Backing (as supplied)	0.030 in. 0.75 mm	0.035 in. 0.9 mm	0.041 in. 1.04 mm	0.030 in. 0.75 mm	0.041 in. 1.04 mm	0.041 in. 1.04 mm
Backing (fully free recovered)	0.039 in. 1.0 mm	0.047 in. 1.2 mm	0.055 in. 1.4 mm	0.039 in. 1.0 mm	0.055 in. 1.4 mm	0.055 in. 1.4 mm
Adhesive (as supplied)	0.039 in. 1.0 mm	0.039 in. 1.0 mm	0.039 in. 1.0 mm	0.060 in. 1.5 mm	0.060 in. 1.5 mm	0.071 in. 1.8 mm

Product properties: HTLP

Property	Test method	Typical Value HTLP80
Backing		
Tensile strength	ASTM D-638	3300 psi (22.8 MPa)
Elongation	ASTM D-638	600%
Hardness, Shore D	ASTM D-2240	55
Shrink force	ASTM D-638, 150°C (302°F)	40 psi
Dielectric strength	ASTM D-149	900 volts/mil (35 KV/mm)
Moisture absorption	ASTM D-570	0.04%
Adhesive		
Softening point	ASTM E-28	120°C (248°F)
Lap shear	ASTM D-1002	750 psi @ 23°C (73°F) 65 psi @ 80°C (176°F)
	EN 12068, @ 10 mm (0.40")/min.	0.19 N/mm ² @ 80°C (176°F)
Sleeve		
Peel to Steel	ASTM D-1000 EN 12068, @ 10 mm (0.40")/min.	40 lbs/in. width 7.7 N/mm
Cathodic disbondment	ASTM G-42, 30 days	12 mm radius @ 80°C (176°F)
Hot water immersion	ASTM D-870, 120 days	no delamination, no blisters or water ingress, @ 80°C (176°F)
Soil stress creep resistance	TP-206 80°C (176°F)	0.003 mm (0.0001 in.)
Low temperature flexibility	ASTM D-2671-C	-25°C (-13°F)
Impact resistance	ASTM G-14 EN 12068, class C	95 in-lbs > 15 Nm *
Penetration resistance	ASTM G-17, @ 80°C EN 12068, Class C	no holidays @ 10.000 volts > 0.6 mm * @ 80°C (176°F)

* Construction /1.2-1 or thicker

Ordering information

HTLP type products are available:

- as cut piece (pre-cut sleeve with separate closure patch)
- as Uni-sleeve (pre-cut sleeve with pre-attached closure patch)
- as a roll (closure patches to be ordered separately)




Select sleeve width that will overlap onto the mill-applied coating by **2 inches** (50 mm) minimum on each side of the weld joint. Take a 10% shrinkage during installation of sleeve width into account when calculating the minimum sleeve width.

* Cut piece / Uni-sleeve

Example: HTLP80-16000X17/B (UNI)

Standard Ordering options		
16000	Outside pipe diameter in mills	2.375" – 100.000" (DN50 – DN2500)
17	Sleeve width in inches (Sw)	11" (11.25 or 285 mm) ⁽¹⁾⁽²⁾ , 17" (17.75 or 450 mm) ⁽¹⁾ , 20" (20.25 or 514 mm) ⁽¹⁾⁽²⁾ 24" (23.5 or 600 mm) ⁽¹⁾ , 34" (34.25 or 870 mm) ⁽¹⁾
/B	Product thickness	/B, /1-1.5, /1.2-1, /1.4-1, /C, /1.4-1.8
/UNI	Designates pre-attached closure	Optional




⁽¹⁾ nominal width ⁽²⁾ not standard in all countries

* Roll form (closure patches to be ordered separately)

Example: HTLP80-20x100/1-1.5-RL

Standard Ordering options		
20	Roll width in inches (Sw)	11" (11.25 or 285 mm) ⁽¹⁾⁽²⁾ , 17" (17.75 or 450 mm) ⁽¹⁾ , 20" (20.25 or 514 mm) ⁽¹⁾⁽²⁾ 24" (23.5 or 600 mm) ⁽¹⁾ , 34" (34.25 or 870 mm) ⁽¹⁾
100	Roll length in feet (Sl)	100 ft (= 30 m), 66 ft (= 20 m, for 34" (870 mm) width)
/1-1.5	Product thickness	/B, /1-1.5, /1.2-1, /1.4-1, /C, /1.4-1.8




⁽¹⁾ nominal width ⁽²⁾ not standard in all countries

* Closure patch

Example: WPCP-IV-4X17

4	Closure patch width in inches (Pw)	4" (100 mm), 6" (150 mm), 8" (200 mm)
17	Closure patch length in inches (Pl)	11" (11.25 or 285 mm) ⁽¹⁾⁽²⁾ , 17" (17.75 or 450 mm) ⁽¹⁾ , 20" (20.25 or 514 mm) ⁽¹⁾⁽²⁾ 24" (23.5 or 600 mm) ⁽¹⁾ , 34" (34.25 or 870 mm) ⁽¹⁾



⁽¹⁾ nominal width ⁽²⁾ not standard in all countries

Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see latest application table AT-GIRTHWELD. For proper product installation, see latest installation instruction.

HTLP type products are installed with epoxy primer: HTLP80 is installed with S1301-M or S1401 primer.

Epoxy Primers are ordered separately. For more ordering information on epoxy primers see latest DS-S1239, DS-S1301M and DS-S1401. As field application of primers may vary, consult a Berry Plastics CPG Representative or Authorized Distributor for rate of coverage guidance

BERRY
PLASTICS CORPORATION
AND SUBSIDIARIES
CORROSION PROTECTION GROUP
www.berrycpg.com

The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics' written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics' liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

Local Distributor / Representative:

For contact details of local Distributors / Representatives
Please visit www.berrycpg.com.

Headquarters
Franklin, MA, USA
Tel: +1 508 918 1714
US Toll Free: +1 800 248 0149
Fax: +1 508 918 1910
CPG@berrypastics.com

Houston, TX, USA
Tel: +1 713 676 0085
US Toll Free: +1 888 676 7202
Fax: +1 713 676 0086
CPGH@berrypastics.com

Tijuana, Mexico
Tel USA +1 858 633 9797
Fax US: +1 858 633 9740
Tel Mexico: +52 664 647 4397
Fax Mexico: +52 664 607 9105
CPGTJ@berrypastics.com

Westerlo, Belgium
Tel: +32 14 722500
Fax +32 14 722570
CPGE@berrypastics.com

Baroda, India
Tel: +91 2667 264721
Fax: +91 2667 264724
CPGIN@berrypastics.com