

# AMERLOCK® 2 VOC

## DESCRIPTION

VOC Compliant Fast Dry, High Solids Epoxy Coating

## PRINCIPAL CHARACTERISTICS

- Fast drying properties
- VOC compliant for <100 g/L specifications
- High performance coating for new or old steel
- Self Priming in many applications
- Compatible with prepared, damp surfaces
- Compatible with adherent rust remaining on prepared surfaces
- Dry temperature resistance up to 450°F on insulated or uninsulated surfaces when mixed with AMERCOAT 880 glass flake additive

## COLOR AND GLOSS LEVEL

- Standard primer colors and custom colors
- Semi-gloss

Note: Epoxy coatings will chalk and fade with exposure to sunlight. Light colors are prone to ambering to some extent. Note that product tinted to custom colors are not recommended for immersion service. Only use factory grind batches for immersion

## BASIC DATA AT 68°F (20°C)

Data for mixed product	
Number of components	Two
Volume solids	83 ± 2%
VOC (Supplied)	max. 0.7 lb/US gal (approx. 84 g/l)
Temperature resistance (Continuous)	To 250°F (121°C)
Temperature resistance (Intermittent)	To 350°F (177°C)
Recommended dry film thickness	4.0 - 8.0 mils (100 - 200 µm) depending on system
Theoretical spreading rate	333 ft <sup>2</sup> /US gal for 4.0 mils (8.3 m <sup>2</sup> /l for 100 µm)
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

### Notes:

- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time
- Color will drift at elevated temperatures
- Intermittent temperature resistance should be less than 5% of the time, and maximum 24 hours



# AMERLOCK® 2 VOC

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Coating performance is, in general, proportional to the degree of surface preparation
- 

### **Steel**

- Remove weld spatter, protrusions, and laminations in steel. Grind welds smooth in accordance with NACE RP-0178
  - Remove all surface contaminants, oil and grease in accordance with SSPC SP-1
  - Abrasive blast with an angular abrasive to an SSPC SP-10 cleanliness or higher for tank lining service. Achieve a surface profile of 2.0 – 4.0 mils (50 – 100 µm)
  - For atmospheric service, abrasive blast to SSPC SP-6 standards
  - The product may be applied over an SSPC SP-12 WJ-2(L) for non-tank lining applications where a previous blast profile can be exposed.
  - For maintenance and repair in atmospheric service, the product can be applied over surfaces prepared in accordance with SSPC SP-2 or SSPC SP-3 (hand and power tool cleaning).
  - AMERCOAT 114 A may be used as a pit filler for severely pitted steel and surface discontinuities
  - Check with PPG technical service for the maximum allowable soluble salt level for water immersion service. This will vary based on the water chemistry and service temperatures
- 

### **Concrete**

- Prepare the surface in accordance with SSPC SP-13 standards
  - Abrade surface per ASTM D-4259 to remove all efflorescence and laitance, to expose subsurface voids, and to provide a surface roughness equivalent of 60 grit sandpaper or coarser
  - Test for moisture by conducting a plastic sheet test in accordance with ASTM D4263
  - Fill voids as necessary with AMERCOAT 114 A epoxy filler
  - For slabs on grade, test for moisture in accordance with ASTM F1869 (calcium chloride test)
  - The maximum allowable moisture transmission is 3 lbs / 1,000 ft<sup>2</sup>/24 hours. Refer to Information Sheet 1496ACUS for further details regarding moisture measurements
- 

### **Galvanized steel**

- Remove oil or soap film with detergent or emulsion cleaner
  - Lightly abrasive blast with a fine abrasive in accordance with SSPC SP-16 guidelines to achieve a profile of 1.5 – 3.0 mils (38 – 75 µm). When light abrasive blasting is not possible, galvanizing can be treated with a suitable zinc phosphate conversion coating.
  - Galvanizing that has at least 12 months of exterior weathering and has a rough surface with white rust present may be over-coated after power washing and cleaning to remove white rust and other contaminants
  - The surface must have a measurable profile
  - A test patch is recommended to determine compatibility and adhesion
  - Not recommended over chromate sealed galvanizing without blasting to thoroughly remove chromates. Adhesion problems may occur
- 

### **Non-ferrous metals and stainless steel**

- Abrasive blast in accordance with SSPC SP-16 guidelines to achieve a uniform and dense 1.5-4.0 mil anchor profile. Size and hardness of abrasive should be adjusted as necessary based on the hardness of the substrate
  - Aluminum may be treated with a surface treatment compliant with Mil-DTL-5541 or equivalent (non-immersion applications only).
-

# AMERLOCK® 2 VOC

## **Aged coatings and repairs**

- All surfaces must be clean, dry, tightly bonded and free of all loose paint, corrosion products or chalky residue
  - Abrade surface, or clean with PREP 88. This product is compatible over most types of properly applied and tightly adhering coatings, however, a test patch is recommended to confirm compatibility
- 

## **Repair**

- Ensure the coating system is sound and well adhered
  - Do not apply over acrylic coatings or coatings that exhibit poor solvent resistance
  - A test patch is recommended to determine compatibility and adhesion
  - Sweep blast or otherwise thoroughly abrade the existing coating in accordance with SSPC SP-7
  - Alternately, PREP 88 may be used to prepare some existing coatings. Please refer to PREP 88 data sheet for details
  - Feather the edges of tightly adhered, in-tact coatings at the perimeter of repair areas
  - Power tool clean the existing steel in accordance with SSPC SP-3 (atmospheric service) or SSPC SP-11 (immersion service)
- 

## **Substrate temperature and application conditions**

- Surface temperature during application should be between 20°F (-7°C) and 122°F (50°C)
  - Surface temperature during application should be at least 5°F (3°C) above dew point
  - Ambient temperature during application and curing should be between 20°F (-7°C) and 122°F (50°C)
  - Relative humidity during application should be above 0% and below 90%
- 

## **SYSTEM SPECIFICATION**

- Primers: Direct to substrate; DIMETCOTE- Series Primers, AMERCOAT 68HS, AMERCOAT 68MCZ
  - Topcoats: AMERCOAT 450-Series Polyurethanes, AMERSHIELD VOC, PSX 700, PSX One
- 

## **INSTRUCTIONS FOR USE**

### **Mixing ratio by volume: base to hardener 50:50 (1:1)**

- Pre-mix base component with a pneumatic air mixer at moderate speeds to homogenize the container. Add hardener to base and agitate with a power mixer for 1-2 minutes until completely dispersed
- 

### **Induction time**

15 minutes

---

### **Pot life**

1 hour at 70°F (21°C)

Note: See ADDITIONAL DATA – Pot life

---



# AMERLOCK® 2 VOC

---

## **Application**

- Area should be sheltered from airborne particulates and pollutants
- Avoid combustion gases or other sources of carbon dioxide that may promote amine blush and ambering of light colors
- Ensure good ventilation during application and curing
- Provide shelter to prevent wind from affecting spray patterns
- PPG 97-739 and tert-butyl acetate are VOC exempt thinners which can be used without limit to maintain < 100 g/L. The following thinners may be used up to 2.5 oz. per gallon to maintain a VOC of < 100 g/L.

## **Material temperature**

Material temperature during application should be between 40°F (4°C) and 90°F (32°C)

---

## **Air spray**

- Use standard conventional equipment

## **Recommended thinner**

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C))

## **Volume of thinner**

0 - 20%

## **Nozzle orifice**

Approx. 0.070 in (1.8 mm)

---

## **Airless spray**

- 45:1 pump or larger
- Can be applied with plural component equipment

## **Recommended thinner**

THINNER 21-06 (AMERCOAT 65) (xylene), THINNER 21-25 (AMERCOAT 101) (recommended for > 90°F (32°C))

## **Volume of thinner**

0 - 5%, depending on required thickness and application conditions

## **Nozzle orifice**

0.017 – 0.019 in (approx. 0.43 – 0.48 mm)

---

# AMERLOCK® 2 VOC

**Brush/roller**

- Use a high quality natural bristle brush and/or solvent resistant, 3/8" nap roller. Ensure brush/roller is well loaded to avoid air entrainment. Multiple coats may be necessary to achieve adequate film-build

**Recommended thinner**

Thinner 21-06 (Amercoat 65, 97-727, xylene) or Thinner 21-25 (Amercoat 101) for temperatures > 90 F.

**Volume of thinner**

Up to 5% THINNER can be added if desired

**Cleaning solvent**

AMERCOAT 12, 12E, or 12V Cleaner, 97-739, AMERCOAT 911 or AMERCOAT 65 thinner (xylene)

**ADDITIONAL DATA**

Overcoating interval for DFT up to 5.0 mils (125 µm)					
Overcoating with...	Interval	32°F (0°C)	50°F (10°C)	70°F (21°C)	90°F (32°C)
itself	Minimum	24 hours	6 hours	3 hours	1.5 hours
	Maximum	3 months	2 months	30 days	14 days
urethane and PSX	Minimum	24 hours	6 hours	3 hours	1.5 hours
	Maximum	30 days	14 days	7 days	4 days

**Notes:**

- Dry times are dependent on air and surface temperatures as well as film thickness, ventilation, and relative humidity. Maximum recoating time is highly dependent upon actual surface temperatures – not simply air temperatures. Surface temperatures should be monitored, especially with sun-exposed or otherwise heated surfaces. Higher surface temperatures shorten the maximum recoat window
- Surface must be clean and dry. Any contamination must be identified and removed. A detergent wash with PREP 88 or equivalent is required prior to application of topcoats after 30 days of exposure. However, particular attention must be paid to surfaces exposed to sunlight where chalking may be present. In those situations, a further degree of cleaning may be required. PPG Technical Service can advise on suitable cleaning methods. If maximum recoat/topcoat time is exceeded, then roughen surface.

Curing time for DFT up to 5.0 mils (125 µm )			
Substrate temperature	Dry to touch	Dry to handle	Service- water immersion
32°F (0°C)	24 hours	38 hours	21 days
50°F (10°C)	8 hours	13 hours	7 days
70°F (21°C)	2 hours	4.5 hours	3 days
90°F (32°C)	1 hour	2 hours	48 hours



# AMERLOCK® 2 VOC

Pot life (at application viscosity)	
Mixed product temperature	Pot life
50°F (10°C)	2 hours
70°F (21°C)	1 hour
90°F (32°C)	30 minutes - 45 minutes

Note: AMERCOAT 8 thinner can be used to extend pot life approximately 10 - 20% in hot weather conditions

## Product Qualifications

- Compliant with USDA Incidental Food Contact Requirements
- AWWA D102-06 ICS #1, #2, #3, #5
- LEED's compliant for Anti-corrosive Paint category

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD - TOXIC HAZARD	INFORMATION SHEET	1431

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.



# AMERLOCK® 2 VOC

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

Packaging: Available in 2-gallon and 5-gallon kits

Product code	Description
AK2V-1	Buff Base
AK2V-3	White Base
AK2V-9	Black Base
AK2V-23	Pearl Gray Base
AK2V-72	Oxide Red Base
AK2V-81	Safety Yellow Base
AK2V-T1	Deep Tint Base *
AK2V-T2	Light Tint Base *
AK2V-T3	Neutral Tint Base *
AK2V-T5	High Hiding Yellow Tint Base *
AK2V-B	Hardener

Note: \* Tintable using UCD V-Line colorants only