

COVALENCE[®] WPC100M

Product Information

Product description: Covalence[®] WPC100M system is a two-layer wrap-around heat-shrinkable sleeve field-joint coating system for pipeline operating at elevated temperatures.

Construction: Two-layer system

- *First layer:* Visco-elastic butyl based adhesive.
- *Second layer:* Radiation cross-linked, high density polyethylene with permanent Change Indicator (PCI).

The WPC100M is compatible with most commonly used steel pipe coatings and is used for offshore and onshore girth weld protection or to recoat (rehabilitate) long pipe sections and large radius bends. The installation is carried out directly on the cleaned and pre-heated pipe surface without any primer required. During installation, the heat-shrinkable sleeve is wrapped around and shrunk to form a tight fit around the joint. During recovery, the adhesive softens and flows to form a perfect bond with the pipe surface providing protection against corrosion. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

Features:

- Low preheat sensitivity & proven functionality.
- Covers a wide range of operating temperature ratings.
- Very good low temperature flexibility for installations in cold climates.
- No special equipment (standard gas torch & a roller).
- Dimpled backing provides a “permanent change” indicator for application of heat.

Benefits:

- Installation friendly in combination with high functional performance.
- No shelf life issues.
- Offers the optimum barrier protection against corrosion.
- Makes installation fast and easy. Keeps installation costs low.
- Dimpled backing allows easy post-heat inspection and offers a reliable inspectability at any time.

Product properties

Backing		
Property	Test method	Typical value
Tensile strength at break	ASTM D-638	3300 psi (22.8 MPa)
Elongation at break	ASTM D-638	600 %
Hardness, Shore D	ASTM D-2240	57
Shrink force	ASTM D-638, @150°C (302°F)	40 psi
Dielectric Strength	ASTM D-49	900 V/mil (35 kV/mm)
Moisture absorption	ASTM D-570	0.04%
Adhesive		
Property	Test method	Typical value
Softening Point	ASTM E-28	155°C (311°F)
Lap shear	ASTM D-1002	47 psi @ 23°C (73°F) 5 psi @ 80°C (176°F)
	EN 12068	0.11 N/mm ² @ 23°C (73°F) 0.005 N/mm ² @ 80°C (176°F)
Installed sleeve		
Property	Test method-	Typical value
Peel to Steel	ASTM D-1000	42 pli
	EN 12068 @ 10 mm/min	0.7 N/mm
	DIN30672 @ 100 mm/min	4.8 N/mm
Cathodic disbondment	EN12968, 28 days	14 mm
	ASTM G-42 @ 80C (176°F), 30 days	17 mm
Low temperature flexibility	ASTM D-2671, C	-40°C (-40°F)
Impact resistance	ASTM G-14	64 in lbf
	EN12068 class C	> 8 J > 15 J *
Penetration resistance	ASTM G-17 @ 65°C (149°F)	No holidays @ 10,000 v
Indentation resistance	EN 12068, Class C, @ 80°C (176°F)	Residual thickness > 0.6 mm *

* Construction /C or thicker

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications.

Product selection guide

Max operating temperature	80°C (179°F) For offshore applications max. operating temperature 100°C (212°F)
Compatible line coatings	PE, PP, FBE, Asphalt Enamel, Tape & Coal Tar
Min. preheat temperature	100°C (212°F)
Recommended pipe preparation	ST2 ½ - ST3 or SA2 ½
Soil stress restrictions	Moderate

Product thickness

	-	/C*
Backing as supplied	0.75 mm (0.030 in)	1.04 mm (0.041 in)
Backing fully free recovered	1.00 mm (0.039 in)	1.40 mm (0.055 in)
Adhesive as supplied	1.00 mm (0.039 in)	1.50 mm (0.060 in)

* Minimum order quantities apply

Ordering information			General information	
Covalence® WPC100M products are available <ul style="list-style-type: none"> – As cut piece (pre-cut with separate closure patch) – As Uni-sleeve (pre-cut with attached closure patch) – As a roll (closure patches to be ordered separately) Select sleeve width that will overlap onto the mill-applied coating by 50 mm (2 inches) minimum on each side of the weld joint. Take a 10% shrinkage during installation of sleeve into account when calculating minimum sleeve width.			Product dimension Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see latest application table AT-GIRTHWELD.	
			Installation guide For proper product installation, see latest application guideline.	
			Handling Handle with care. Keep boxes upright.	
			Storage Store indoor, clean and dry, away from direct sunlight in a cool place below +50°C. Unlimited shelf life.	
			Documentation Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to info@sealforlife.com	
			Certified staff Application of the described coating system should be carried out by certified personnel.	
Cut piece / Uni-sleeve				
Example	WPC100M-16000X17/C(UNI)			
	Designation	Standard ordering options		
16000	Outside pipe diameter	2.375" – 100.000" (DN50 – DN2500)		
17	Sleeve width (in)	17 (17.75" or 450 mm)* 20 (20.25" or 514 mm)* 24 (23.50" or 600 mm)*		
/C	Product thickness	-, /C		
UNI	Designates pre-attached closure patch	Optional		
			* nominal width	
Roll form (closure patch to be ordered separately)				
Example	WPC100M-20X100-RL			
	Designation	Standard ordering options		
20	Sleeve width (in)	17 (17.75" or 450 mm)* 20 (20.25" or 514 mm)* 24 (23.50" or 600 mm)*		
100	Roll length	100 ft (= 30 m)		
-	Product thickness	-, /C		
			* nominal width	
Closure patches (to be ordered separately)				
Example	WPCP-IV-4X17			
	Designation	Standard ordering options		
4	Patch width (in)	4 (100 mm) 6 (150 mm) 8 (200 mm)		
17	Patch length (in)	17 (17.75" or 450 mm)* 20 (20.25" or 514 mm)* 24 (23.50" or 600 mm)*		
			* nominal width	



Seal For Life Industries LLC
Franklin, MA, USA
Tel: +1 508 918 1600
Toll Free: +1 800 248 7659
Fax: +1 508 918 1905
franklin@sealforlife.com

Seal For Life Industries
Tijuana, Mexico
Tel USA: +1 658 633 9797
Fax USA: +1 858 633 9740
Tel Mx: +52 664 647 4397
Fax Mx: +52 664 607 9105
mexico@sealforlife.com

Seal For Life Industries
Stopaq B.V.
Stadskanaal, the Netherlands
Tel: +31 599 696 170
Fax: +31 599 696 177
info@sealforlife.com

Seal For Life Industries BVBA
Westerlo, Belgium
Tel: +32 14 722 500
Fax: +32 14 722 570
belgium@sealforlife.com

Seal For Life Private Ltd.
Baroda, India
Tel: +91 2667 264 721
Fax: +91 2667 264 724
india@sealforlife.com

Anodefex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr® - Elasto.Qote®

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries liability is stated in the standard terms and conditions of sale. Seal For Life Industries makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Covalence® is a registered trademark of Seal For Life Industries.