

COVALENCE® WPCT

Product Information

WPCT is a two-layer field-joint coating system for corrosion protection of pipelines operating at ambient temperature and elevated temperatures.

Product description: Covalence® WPCT is a wraparound heat-shrinkable, ready-to-fit assembly for the corrosion protection of field girth weld joints in distribution and transmission systems. WPCT is compatible with standard pipe coatings. WPCT can also be used for coating bare, replacement pipe sections and large radius bends. The system is designed to be applied with minimum preheating and is ideal for large diameter water pipe.

Construction: Two-layer system

- *First layer:* Visco-elastic butyl based low preheat adhesive.
- *Second layer:* Radiation-cross-linked, high density polyethylene with PCI (Permanent Change Indicator).

The installation is carried out directly on the cleaned and dried (pre-heated) pipe surface without any primer being required. During installation, the heat-shrinkable sleeve is wrapped and shrunk to form a tight fit around the joint. During recovery, the adhesive softens and flows to form a perfect bond with the pipe surface providing protection against corrosion. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

Features:

- Low preheat sensitivity & proven functionality.
- Excellent aging performance.
- Superior cathodic disbondment and hot water immersion resistance.
- Dimpled backing provides a “permanent change” indicator for application of heat.
- No special equipment or skills required (standard gas torch & roller)
- Self-healing effect. Saves extra intervention steps.

Benefits:

- Installation friendly in combination with high functional performance.
- No shelf life issues.
- Offers the optimum barrier protection against corrosion.
- Dimpled backing allows easy post-heat inspection and offers a reliable inspectability at any time.
- Makes installation fast and easy. Keeps installation costs low.
- Tough, but flexible even at low temperatures!

Product properties

Backing

| Property | Test method | Typical value |
|----------------------------------|------------------------------|-----------------------|
| Tensile strength at break | ASTM D638 | 3300 psi 22.8 MPa |
| Elongation at break | ASTM D638 | 600 % |
| Hardness, Shore D | ASTM D2240 | 57 |
| Shrink force | ASTM D638 @ 150°C (302°F) | 40 psi |
| Dielectric Strength | ASTM D149 | 900 V/mil 35 kV/mm |
| Water absorption | ISO 62 | 0.04% |

Adhesive

| Property | Test method | Typical value |
|------------------------|---|-----------------------------------|
| Softening point | ASTM E28 | 134°C (273°F) |
| Lap shear | ASTM D1002 EN 12068/ @ 10 mm /min | 50 psi > 0.1 N/mm ² |

Installed sleeve

| Property | Test method | Typical value |
|------------------------------------|--|---|
| Peel to Steel | ASTM D1000 EN 12068 @ 10 mm /min | 50 lb/in 1.1 N/mm |
| Cathodic disbondment | ASTM G42 @65°C(149°F), 30 days | 7 mm radius |
| Hot water immersion | ASTM D870 @ 65°C (149°F), 120 days | No delamination, no blisters or water ingress |
| Impact resistance | ASTM G14 EN 12068 | 80 in.lb >8 J |
| Indentation resistance | ASTM G17 EN 12068, Class B30 | No holiday with 10 kV detector >0.6 mm remaining thickness |
| Low temperature flexibility | ASTM D2671, procedure C | -14°C (6.8°F) |

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications.

Product selection guide

| | |
|-------------------------------------|---|
| Max operating temperature | 65°C (149°F) |
| Compatible line coatings | PE, PP, FBE, PU, Tape, Coal Tar & Asphalt |
| Min. preheat temperature | 60°C (140°F) |
| Recommended pipe preparation | ST2 ½ -ST3 or SA2 ½ |
| Soil stress restrictions | Moderate |
| Performance | EN12068 Class B30, AWWA-C-216 |

Product thickness

| | WPCT |
|-------------------------------------|-----------------------|
| Backing as supplied | 0.75 mm (0.030 in) |
| Backing fully free recovered | 1.00 mm (0.039 in) |
| Adhesive as supplied | 1.20 mm (0.047 in) |
| Finished Product as supplied | 1.95 mm (0.077 in) |

| Ordering information | |
|--|--|
| Covalence® WPCT type product are available | |
| <ul style="list-style-type: none"> As Uni-sleeve (pre-cut sleeve with pre-attached closure patch) As a roll (closure patch to be ordered separately) | |
| Min.sleeve width = (bare steel dimension + 50 mm (2") on each side of the fieldjoint) + 10% | |
| Maximum 10% of the supplied rolls can have a splice. Min length of a partial length is 5 M or 15 ft. | |

| Cut piece / Uni-sleeve | |
|------------------------|---|
| Example | WPCT-10750X17/UNI |
| Designation | Standard ordering options |
| 10750 | Outside pipe diameter (mils) 2.375 – 68.000 (DN50-DN1700) |
| 17 | Sleeve width (in) 11 (11.25" or 285 mm)* 17 (17.75" or 450 mm)* 24 (23.625" or 600 mm)* 34 (34.25" or 870 mm)* <i>* nominal width</i> |
| /UNI | Designates pre-attached closure patch Optional |

| Roll form (closure patch to be ordered separately) | |
|--|---|
| Example | WPCT-17X100-RL |
| Designation | Standard ordering options |
| 17 | Sleeve width (in) 11 (11.25" or 285 mm)* 17 (17.75" or 450 mm)* 24 (23.625" or 600 mm)* 34 (34.25" or 870 mm)* <i>* nominal width</i> |
| 100 | Roll length (ft) 100 (30 m) |

Rolls can have a splice. Max 10% of the roll order will have a splice. Min partial length will be 5M or 15 ft.

| Closure patches (to be ordered separately) | |
|--|--|
| Example | WPCP-IV-4X17 |
| Designation | Standard ordering options |
| 4 | Patch width (in) 4 (100 mm), 6 (150 mm), 8 (200 mm) |
| 17 | Patch length (in) 11 (11.25" or 285 mm)* 17 (17.75" or 450 mm)* 24 (23.625" or 600 mm)* 34 (34.25" or 870 mm)* <i>* nominal length</i> |

| General information | |
|---------------------------|--|
| Product dimension | Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see latest application table AT-GIRTHWELD. |
| Installation guide | For proper product installation, see latest installation instruction. |
| Handling | Handle with care. Keep boxes upright. |
| Storage | Store indoor, clean and dry, away from direct sunlight in a cool place at temperatures between 0°C (32°F) and +50°C (122°F). Unlimited shelf life. |

| Information | |
|------------------------|---|
| Documentation | Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to info@sealforlife.com |
| Certified staff | Application of the described coating system shall be carried out by certified personnel. |



Seal For Life Industries LLC
Franklin, MA, USA
Tel: +1 508 918 1600
Toll Free: +1 800 248 7659
Fax: +1 508 918 1905
franklin@sealforlife.com

Seal For Life Industries Mexico
S de R.L. de C.V.
Tijuana, Mexico
Tel USA: +1 858 633 9797
Fax USA: +1 858 633 9740
Tel Mx: +52 664 647 4397
Fax Mx: +52 664 607 9105
mexico@sealforlife.com

Seal For Life Industries
Stopaq B.V.
Stadskanaal, the Netherlands
Tel: +31 599 696 170
Fax: +31 599 696 177
info@sealforlife.com

Seal For Life Industries BVBA
Westerlo, Belgium
Tel: +32 14 722 500
Fax: +32 14 722 570
belgium@sealforlife.com

Seal For Life India Private Ltd.
Baroda, India
Tel: +91 2667 264 721
Fax: +91 2667 264 724
india@sealforlife.com

Anodefex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr® - Easy.Qote®

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries liability is stated in the standard terms and conditions of sale. Seal For Life Industries makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Covalence® is a registered trademark of Seal For Life Industries.